

Test Report

Report No.: SHT09022500322

Page 1 of 4

Client : NANTONG GOLDEN PHOENIX TOY MANUFACTURING CO.LTD.
Address : NO.869 NANYUAN MIDDLE ROAD QIDONG CITY JIANGSU CHINA

Report on the submitted sample said to be:

Sample Description : 8" Cowboy Outfit/ Cowboy Outfit
Item/Lot No. : 1150/20039
Country of Origin : China
Exported to : U.S.A
Labelled Age Grading : Over three
Age Group Applied in Testing : Over 3 years
Sample Received Date : Feb.26, 2009
Sample Tested Date : Feb.26, 2009 to Feb.28, 2009

TEST REQUEST

ASTM F963-07^{e1} Standard Consumer Safety Specification for Toy Safety

CONCLUSION

PASS

Test Results: Please refer to next page(s)

Inspected by: Maggie, Approved by: Jacky Chan, Approved date: 2009-02-28
General Manager



Building C, Hongwei Industrial Zone, Baoan 70 District, Shenzhen

Test Report

Report No.: SHT09022500322

Page 2 of 4

ASTM F963 – 07^{e1}

AS SPECIFIED IN ASTM F963-07^{e1} STANDARD CONSUMER SAFETY SPECIFICATION FOR TOY SAFETY.

<u>Clause</u>	<u>Description</u>	<u>Assessment</u>
4.	Safety Requirements	
4.1	Material Quality **.....	Pass
4.2	Flammability Test.....	N/A (See Note 1)
4.3	Toxicology	
4.3.5	Paint & Similar Surface-coating Material.....	Pass (See Note 2)
4.6	Small Objects.....	N/A
4.7	Accessible Edges.....	Pass
4.9	Accessible Points.....	Pass
5.	Safety Labeling Requirements	
5.2	Age Grading Labeling.....	Pass
7.	Producers Markings	
7.1	Producers Markings.....	Pass
8.	Test Method	
8.5	Normal Use Testing	Pass
8.7	Impact Test	Pass
8.8	Torque Test.....	Pass
8.9	Tension Test.....	Pass

**Visual Examination

N/A = Not Applicable

Note 1:

Flammability Test (Clause 4.2)

Flammability Test on Textile MaterialsN/A

The samples are exempt from 16CFR 1610.1(d)(1):plain surface fabric with weight>2.6oz/sq.yd.

N/A = Not Applicable

Building C, Hongwei Industrial Zone, Baoan 70 District, Shenzhen

Test Report

Report No.: SHT09022500322

Page 3 of 4

Note 2 :

ASTM F963-07^{e1} CLAUSE 4.3.5 - PAINT & SIMILAR SURFACE-COATING MATERIAL

Heavy Metals Analysis : Total Lead (Clause 4.3.5.1)

Acid Digestion Method was Used and Total Lead Content was Determined by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

<u>Element</u>	<u>Result(mg/kg)</u>		<u>Limit</u> (mg/kg)
	(1)	(2)	
Total Lead	<5	<5	600

Tested Components:

- (1) Coffee flocking(cloth)
- (2) Black coating(label)

Heavy Metals Analysis : Soluble Heavy Metal (Clause 4.3.5.2)

Acid Extraction Method was Used in accord with ASTM F963-07^{e1} (Clause 8.3) and Toxic Elements Content were Determined by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

<u>Elements</u>	<u>Result (mg/kg)</u>		<u>Limit</u> (mg/kg)
	(1)	(2)	
Soluble Antimony (Sb)	<5	<5	60
Soluble Arsenic (As)	<2.5	<2.5	25
Soluble Barium (Ba)	<5	<5	1000
Soluble Cadmium (Cd)	<5	<5	75
Soluble Chromium (Cr)	<2.5	<2.5	60
Soluble Lead (Pb)	<5	<5	90
Soluble Mercury (Hg)	<2.5	<2.5	60
Soluble Selenium (Se)	<5	<5	500

Tested Components:

- (1) Coffee flocking(cloth)
- (2) Black coating(label) (Sample weight=18.9mg)

Remark:

- < = Less than
- mg/kg = Milligram per kilogram based on dry weight of sample
- Results shown of soluble elements are of adjusted analytical results by subtracting analytical correction factor
- As received, the test portion of black coating(label) is less than 10mg, therefore such components were not tested for soluble elements, as specified in ASTM F963-07^{e1} Clause 8.3.3.1 (2)

Note:

- Only applicable clauses were shown.

Building C, Hongwei Industrial Zone, Baoan 70 District, Shenzhen

Test Report

Report No.: SHT09022500322

Page 4 of 4

Photo of the sample



*** End of report ***

This report is considered invalidated without the Special Seal for Inspection of the CTI, This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of CTI, this test report shall not be copied except in full and published as advertisement.

Building C, Hongwei Industrial Zone, Baoan 70 District, Shenzhen