

Test Report

Report No.: SHT09011000060

Page 1 of 5

Client : NANTONG GOLDEN PHOENIX TOY MANUFACTURING CO.LTD.
Address : NO.869 NANYUAN MIDDLE ROAD QIDONG CITY JIANGSU CHINA

Report on the submitted sample said to be:

Sample Description : Purple & Gold Cheerleader
Item/Lot No. : 20185
Exported to : U.S.A
Labelled Age Grading : Over three
Age Group Applied in Testing : Over three years
Sample Received Date : Jan.13, 2009
Sample Tested Date : Jan.13, 2009 to Jan.20, 2009

TEST REQUEST

- 1) ASTM F963-07^{e1} Standard Consumer Safety Specification for Toy Safety
- 2) US Consumer Products Safety Improvement Act 2008 (CPSIA)(H.R. 4040)
 - Lead Content Test

CONCLUSION

PASS

PASS

Test Results: Please refer to next page(s)

Inspected by: Richard Lau, Approved by: Jacky Chan, Approved date: 2009-01-20
General Manager



Building C, Hongwei Industrial Zone, Baoan 70 District, Shenzhen

Test Report

Report No.: SHT09011000060

Page 2 of 5

1) ASTM F963 – 07^{e1}

AS SPECIFIED IN ASTM F963-07^{e1} STANDARD CONSUMER SAFETY SPECIFICATION FOR TOY SAFETY.

| <u>Clause</u> | <u>Description</u> | <u>Assessment</u> |
|---------------|---|----------------------|
| 4. | Safety Requirements | |
| 4.1 | Material Quality **..... | Pass |
| 4.2 | Flammability Test..... | N/A (See Note 1) |
| 4.3 | Toxicology | |
| 4.3.5 | Paint & Similar Surface-coating Material..... | Pass (See Note 2) |
| 4.6 | Small Objects..... | N/A |
| 4.7 | Accessible Edges..... | Pass |
| 4.9 | Accessible Points..... | Pass |
| 5. | Safety Labeling Requirements | |
| 5.2 | Age Grading Labeling..... | Pass |
| 7. | Producers Markings | |
| 7.1 | Producers Markings..... | Pass |
| 8. | Test Method | |
| 8.5 | Normal Use Testing | Pass |
| 8.7 | Impact Test | Pass |
| 8.8 | Torque Test..... | Pass |
| 8.9 | Tension Test..... | Pass |

**Visual Examination

N/A = Not Applicable

Note 1:

Flammability Test (Clause 4.2)

Flammability Test on Textile Materials.....N/A

The samples are exempt from 16 CFR 1610.1(d)(1):plain surface fabric with weight>2.6OZ/sq.yd.

N/A = Not Applicable

Building C, Hongwei Industrial Zone, Baoan 70 District, Shenzhen

Test Report

Report No.: SHT09011000060

Page 3 of 5

Note 2 :

ASTM F963-07^{e1} CLAUSE 4.3.5 - PAINT & SIMILAR SURFACE-COATING MATERIAL

Heavy Metals Analysis : Total Lead (Clause 4.3.5.1)

Acid Digestion Method was Used and Total Lead Content was Determined by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

| <u>Element</u> | <u>Result(mg/kg)</u> | <u>Limit</u> (mg/kg) |
|----------------|----------------------|-------------------------|
| | Black coating(label) | |
| Total Lead | < 5 | 600 |

Heavy Metals Analysis : Soluble Heavy Metal (Clause 4.3.5.2)

Acid Extraction Method was Used in accord with ASTM F963-07^{e1} (Clause 8.3) and Toxic Elements Content were Determined by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

Remark:

- < = Less Than
- mg/kg = Milligram per kilogram based on dry weight of sample
- As received, the test portion of black coating(label) is less than 10mg, therefore such components were not tested for soluble elements, as specified in ASTM F963-07^{e1} Clause 8.3.3.1 (2)

Note:

- Only applicable clauses were shown.

2) US CONSUMER PRODUCTS SAFETY IMPROVEMENT ACT 2008 (CPSIA)(H.R. 4040)

▼ LEAD CONTENT TEST

As Specified in Consumer Products Safety Improvement Act 2008 (CPSIA)(H.R. 4040) and Title 16 Part 1303 Code of Federal Regulations, Chapter II – Consumer Products Safety Commission of U.S.A, Acid Digestion Method was Used and Total Lead Content was Determined by Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES).

1. Lead content in surface coating(s) and similar materials

| <u>Element</u> | <u>Result (ppm)</u> | <u>Required Limit^{#1}</u> (ppm) |
|----------------|---------------------|---|
| | (1) | |
| Total Lead | <5 | 600 |

Test Report

Report No.: SHT09011000060

Page 4 of 5

2. Lead content in other materials

| Element | Result (ppm) | | | | | | Required Limit ^{#2} |
|------------|--------------|-----|-----|-----|-----|-----|------------------------------|
| | (2) | (3) | (4) | (5) | (6) | (7) | (ppm) |
| Total Lead | <5 | <5 | <5 | <5 | <5 | <5 | 600 |

| Element | Result (ppm) | | | | | Required Limit ^{#2} |
|------------|--------------|-----|------|------|------|------------------------------|
| | (8) | (9) | (10) | (11) | (12) | (ppm) |
| Total Lead | <5 | <5 | <5 | <5 | <5 | 600 |

Tested Components:

- (1) Black coating(label)
- (2) White fabric(label)
- (3) White thread
- (4) White ribbon
- (5) Yellow thread
- (6) Purple thread
- (7) Purple flock
- (8) Yellow flock
- (9) Yellow/white fabric
- (10) White cord
- (11) White flock
- (12) Purple Velcro

Remark:

- < = Less than
- ppm= parts per million based on dry weight of sample
- ^{#1} = The total Lead limit for surface coatings and similar materials will be **90ppm** (Effective Date : August 14, 2009)
- ^{#2} = The total Lead limit for other materials will be **300ppm** (Effective Date : August 14, 2009)

Building C, Hongwei Industrial Zone, Baoan 70 District, Shenzhen

Test Report

Report No.: SHT09011000060

Page 5 of 5

Photo of the sample



*** End of report ***

This report is considered invalidated without the Special Seal for Inspection of the CTI, This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of CTI, this test report shall not be copied except in full and published as advertisement.

Building C, Hongwei Industrial Zone, Baoan 70 District, Shenzhen